# GRAFIWRAP AMD FILMS CAST CARBON

### **REFERENCES CBx05 to CBx81**

**RELEASE 01.10.2020** 



#### **DESCRIPTION**

The GrafiWrap AMD (Automotive & Deco) Carbon series with product references CBx05 up to CBx81 is a structured cast PVC film with a carbon effect. The film comes with a permanent adhesive.

## APPLICATION

**TEST METHOD** 

Thanks to their exceptional smoothness and good deformability GrafiWrap cast carbon films are perfectly suited for vehicle wrapping and for interior design. They can be used for indoor and outdoor applications.

### → INDOOR/OUTDOOR USE

#### **COMPOSITION**

#### **FILM**

 $145\mu m$  structured multi-layered cast PVC film with a carbon effect.

#### **ADHESIVE**

Transparent permanent pressure-sensitive solvent-based acrylic adhesive.

#### **RELEASE LINER**

Structured siliconised white PE-coated paper - 130 g/m², giving the film an air escape effect.

#### **PRODUCT ADVANTAGES**

 The cast carbon films give your design a perfect carbon look.

**RESULT** 

Air escape technology.

#### **PRODUCT SPECIFICATIONS**

**Technical properties** 

**RELATIVE HUMIDITY** 

**TEMPERATURE** 

 $50 \pm 5\%$ 

 $23 + 2^{\circ}C$ 

1	Thickness film (1)
	Thickness film + adhesive + release liner
2	Elongation at break (production length) (2) Elongation at break (cross)
3	Dimensional stability (3)
4	Gloss (minimum – measuring angle 20°)
5	Adhesion strength after 20 minutes (4)
	Adhesion strength after 24 hours
6	Quickstick (5)
7	Max. outdoor life span (unprinted) (6)
8	Temperature range during application
	Temperature range at use
^	Plana de Utana

Din53370	145µm
	340µm
Din53455	> 100%
	> 100%
Finat 14	< 0,2mm
Din67530	Not measurable because of the
	structure of the material
Finat 1	14 N/25mm
	18 N/25mm
Finat 9	14 N
-	Flat/slightly curved surfaces:
	- Adhesion 10 years
	- Colour 7-10 years
	Full wrap: 3-5 years
-	+5°C up to +40°C
	-20°C up to +100°C

If applied on aluminium, glass, steel = self-extinguishing

(1) Average (2) Maximum

(3) Average

(4) Average

(5) Central-European conditions

# GRAFIWRAP AMD FILMS CAST CARBON

## **REFERENCES CBx05 to CBx81**

**RELEASE 01.10.2020** 



#### **STORAGE INSTRUCTIONS**

All GrafiWrap materials always have to be stored in their original packing and with the original protection flanges (preferably vertically).

In order to avoid any loss of quality, the GrafiWrap materials should be stored in suitable conditions, i.e. at a temperature between 10/20°C and a relative humidity of 50%. Under these conditions GrafiWrap materials can be stored for a period of two years.

#### **COLOUR OF THE FILM**

The colour of the GrafiWrap film may come off slightly because of over-pigmentation, but as the film is coloured in the mass, this will have no influence on the UV-resistance and the eventual colour of the film.

As the colour of the film can differ slightly for each production run, we advise you not to use films with different batch numbers in one single and critical job. The number to be taken into consideration for this purpose consists of the first 5 numbers of the 7-digit batch number.

#### **APPLICATION**

When applying structured films, it is important that the right techniques are used for heating the material. More "tips & tricks" on the application of the structured GrafiWrap films can be found on our website (www.grafityp.com → Downloads → Manuals).

#### **REMOVAL**

In order to remove the film again, it should be heated thoroughly in order to prevent adhesive transfer. Due to the structure of the material, the film can tear while being removed.

#### **IMPORTANT**

The information mentioned in this product data sheet is based upon tests that were executed by Grafityp, and that we consider to be reliable. The information always represents an average, a minimum or a maximum value, and should be considered as such. It is given only for your information, and does not give any guarantee. It is up to the end user to decide whether or not the product is suited for his particular application.

The expected outdoor life span refers to outdoor use under Central European conditions and to vertical application. Non-vertical application can reduce the life span up to 50%. The expected life span of our films is based upon professional application on a dry, degreased and suitable background. Tropical conditions, or the use near chemical emission, may have a detrimental effect on the life span.

The life span can also differ, depending on the colour (due to the pigmentation).

More information on this in our warranty certificates.

GrafiWrap films must only be applied to undamaged, original paintwork. Grafityp cannot be held responsible for any damage during application or removal, if the material is used on non-original or aftermarket paintwork.

Subject to modifications.