

PRODUCT DATA SHEET

GRAFITACK ETCHED GLASS FILM

REFERENCE EFTR01

RELEASE 25.09.2020

GRAFITYP
makes you stick

DESCRIPTION

Grafitack etched glass film EFTR01 is a satin pvc-free polyolefine-based Grafityp Ecology Film (GEF), without chlorine or plasticizers.

COMPOSITION

FILM

100µm satin ecological pvc-free film.

ADHESIVE

Permanent pressure-sensitive dispersion-based acrylic adhesive with a high resistance against UV-radiation, chemical products and humidity.

RELEASE LINER

PE-coated paper of 120 g/m².

APPLICATION

Grafitack etched glass film EFTR01 enables you to create the most stunning decorations on mirrors, glass doors, shop windows, etc... The film is suited for wet application.

→ INDOOR/OUTDOOR USE

PRODUCT ADVANTAGES

- Ecological alternative to sandblasting (no chlorine, no plasticizers).
- No chlorine gas is released when incinerated.
- Extremely flexible.
- Hardly any shrinkage.

PRODUCT SPECIFICATIONS

Technical properties

RELATIVE HUMIDITY

50 ± 5%

TEMPERATURE

23 ± 2°C

	TEST METHOD	RESULT
1 Thickness film (1) Thickness film + adhesive + release liner	Din53370	100µm 260µm
2 Elongation at break (production length) (2) Elongation at break (cross)	Din53455	> 500% > 500%
3 Dimensional stability (3)	Finat 14	< 0,20mm
4 Gloss (Maximum – measuring angle 60°)	Din67530	< 20 Gloss Units
5 Adhesion strength after 20 minutes (4) Adhesion strength after 24 hours	Finat 1	8 N/25mm 12 N/25mm
6 Quickstick (5)	Finat 9	8 N
7 Max. outdoor life span (6)	-	4 years
8 Temperature range during application Temperature range at use	-	+5°C up to +40°C -15°C up to +90°C
9 Flammability If applied on aluminium, glass, steel = self-extinguishing		

(1) Average (2) Minimum (3) Maximum (4) Average (5) Average (6) Central-European conditions

PRODUCT DATA SHEET

GRAFITACK ETCHED GLASS FILM

REFERENCE EFTR01

RELEASE 25.09.2020

GRAFITYP
makes you stick

STORAGE INSTRUCTIONS

All Graftack materials always have to be stored in their original packing and with the original protection flanges (preferably vertically).

In order to avoid any loss of quality, the Graftack materials should be stored in suitable conditions, i.e. at a temperature between 10/20°C and a relative humidity of 50%. Under these conditions Graftack materials can be stored for a period up to two years.

REMOVAL

If you wish to remove the film, we advise you to use a heat gun. If any glue residues stay behind on the glass surface after taking off the film, you can simply remove them by moistening them with soap-water. Leave this to soak in for a couple of minutes, and then chip it off by means of a steel scraper (also used for removing paint stains).

IMPORTANT

The information mentioned in this product data sheet is based upon tests that were executed by Graftyp, and that we consider to be reliable. The information always represents an average, a minimum or a maximum value, and should be considered as such. It is given only for your information, and does not give any guarantee. It is up to the end user to decide whether or not the product is suited for his particular application.

The expected outdoor life span refers to outdoor use under Central European conditions and to vertical applications. Non-vertical application can reduce the life span up to 50%. The expected outdoor life span of our films is based upon professional application on a dry, degreased and suitable background. Tropical conditions, or the use near chemical emission, may have a detrimental effect on the life span.

For more information, see our warranty certificates.

Subject to modifications.

SURFACE CLEANING

In order to achieve an optimal result, we advise you to clean/degrease the surface with isopropanol and/or to use a low-tack application tape!

VINYL COLOUR

As the colour of the film can differ slightly for each production run, we advise you not to use films with different batch numbers in one single and critical job. The number to be taken into consideration for this purpose consists of the first 5 numbers of the 7-digit batch number.

END OF LIFE

By the end of the pvc-free film's life span, small cracks may appear in the polymeric layer, as a result of which the film can no longer be removed in one piece.